



Makrofol DE 1-1

PC films, standard / Not filled, surfaces with and without texturing

PC-film, transparent, both sides gloss, thickness 125 - 750 micron, one or both sides either with cling (C) or stick (S) masking.

ISO Shortname

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Shrinkage, parallel	130 °C; 1 h	%	IEC 60674	0,4
Shrinkage, across	130 °C; 1 h	%	IEC 60674	0,4
Mechanical properties (23 °C/50 % r.h.)				
Tensile modulus		MPa	ISO 527-1,-3	2200
C Stress at break, parallel		MPa	ISO 527-1,-3	70
C Stress at break, across		MPa	ISO 527-1,-3	70
Strain at break		%	ISO 527-1,-3	150
Thermal properties				
Coefficient of linear thermal expansion, parallel	20 to 120 °C	10 ⁻⁶ /K	DIN 53752	70
Coefficient of linear thermal expansion, transverse	20 to 120 °C	10 ⁻⁶ /K	DIN 53752	70
Burning rate (US-FMVSS)		mm/min	ISO 3795	<= 100
Electrical properties (23 °C/50 % r.h.)				
C Relative permittivity	1 MHz	-	IEC 60250	3.0
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	100
Electrolytic corrosion		Rating	IEC 60426	A1
Other properties (23 °C)				
C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	0,2
C Density		kg/m ³	ISO 1183	1200
Material specific properties				
Luminous transmittance (clear transparent materials)	Type of light; C/2; O/D	%	ISO 13468-2	> 80



Makrofol DE 1-1

Disclaimer

Disclaimer for Sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Publisher: Business Development Plastics

Bayer MaterialScience AG,

D-51368 Leverkusen,

www.bayermaterialscience.com