

# Bayfol CR 6-2

**PC-blend films / Increased chemical resistance and dynamical strength**

Dazzle-free, PC/PBT-blend-film with high dynamic strength, increased chemical resistance, good cold formability and high scratch resistance, clear translucent, one side fine velvet, one side very fine matte, thicknesses 125 - 375 microns.

ISO Shortname

Property	Test Condition	Unit	Standard	Value
<b>Rheological properties</b>				
Shrinkage, parallel	90 °C; 1 h	%	IEC 60674	<= 0.4
Shrinkage, across	90 °C; 1 h	%	IEC 60674	<= 0.2
<b>Mechanical properties (23 °C/50 % r.h.)</b>				
Tensile modulus		MPa	ISO 527-1,-3	>= 2100
C Stress at break, parallel		MPa	ISO 527-1,-3	>= 55
C Stress at break, across		MPa	ISO 527-1,-3	>= 55
Strain at break		%	ISO 527-1,-3	>= 120
<b>Thermal properties</b>				
Coefficient of linear thermal expansion, parallel	20 to 120 °C	10 <sup>-6</sup> /K	DIN 53752	80
Coefficient of linear thermal expansion, transverse	20 to 120 °C	10 <sup>-6</sup> /K	DIN 53752	80
<b>Other properties (23 °C)</b>				
Roughness	R3z; Top Side	µm	acc. ISO 4288	5.0
Roughness	R3z; Reverse Side	µm	acc. ISO 4288	13
C Density		kg/m <sup>3</sup>	ISO 1183	1230
C Gloss	60 °; Top Side	-	ISO 2813	25
C Gloss	60 °; Reverse Side	-	ISO 2813	6.0
<b>Material specific properties</b>				
Luminous transmittance (clear transparent materials)	Type of light; C/2; O/D	%	ISO 13468-2	>= 80



## Bayfol CR 6-2

### Disclaimer

Disclaimer for Sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

---

Publisher: Business Development Plastics

Bayer MaterialScience AG,

D-51368 Leverkusen,

[www.bayermaterialscience.com](http://www.bayermaterialscience.com)